

INDUSFALT 20/30

DEFINITION:

Asphalt bitumen obtained by direct distillation or other refining methods specially designed to be used as base in industrial products.

SPECIFICATIONS:

Characteristics	Units	Standard	Min.	Max.
Softening point (R&B)	°C	EN 1427	55	63
Penetration (25°C, 100g, 5s)	0,1 mm	EN 1426	20	30
Solubility in xylene	%	EN 12592	99	-
Mass loss	%	EN 13303	-	0,5
Flash point	°C	EN ISO 2592	240	-

APPLICATIONS:

- Raw material for waterproofing products in construction and membranes, joint sealing compounds and asphaltic paints.

RECOMMENDED WORKING TEMPERATURES:

- 120 - 160 °C.