

INDUSFALT BM

Asphalt bitumen designed for the production of polymer modified bitumen.

SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
Original bitumen				
Penetration (25°C; 100g; 5s)	0,1 mm	EN 1426	70	100
Softening point (R&B)	°C	EN 1427	43	51
Fraass point	°C	EN 12593	-	-10
Solubility in xylene	%	EN 12592	99	-
Flash point	°C	EN ISO 2592	230	-
Resistance to hardening at 163°C (EN 12607-1)				
Mass loss	%		--	0,8
Retained penetraci3n (25°C; 100g; 5s)	% p.o.	EN 1426	46	-
Δ Increase in softening point (R&B)	°C	EN 1427	-	11

RECOMMENDED WORKING TEMPERATURES

- > Pumping temperatura (°C): >100.
- > Temperature for polymer modification: 160 - 180.