

MULTYPRO 35/50

Multigrade type high performance bitumen.

SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
Original Binder				
Penetration (25°C; 100g; 5s)	0,1 mm	EN 1426	35	50
Penetration Index	-	EN 12591	0,1	1,5
Softening point	°C	EN 1427	59	69
Fraass Breaking Point	°C	EN 12593	--	-8
Flash point	°C	EN ISO 2592	235	-
RTFOT Residue (EN 12607-1)				
Mass loss	%	EN 12607-1	--	0,5
Retained penetration	%	EN 1426	50	--
Δ Increase in softening point (R&B)	°C	EN 1427	--	10

RECOMMENDED WORKING TEMPERATURES

- > Mixing Temperature (°C): 160 - 170.
- > Binder Temperature (°C): 160 - 170.
- > Compacting Temperature (°C): 155 - 165.
- > Maximum heating temperature (°C): 180.

USES

- > Rutting resistant Asphalt mixes.