

## PINTURASFALT IA-22

### Solvent-based asphaltic paint

Asphalt paint consisting of bitumen and organic solvents. It provides excellent protection to any type of surface. It complies with the national standard UNE 104235 for asphalt paints (type II).

<b>PROPERTIES</b>	<ul style="list-style-type: none"><li>&gt; Easy to apply.</li><li>&gt; Easy to handle.</li><li>&gt; Good adhesion to substrates.</li></ul>
<b>APPLICATIONS</b>	<ul style="list-style-type: none"><li>&gt; Priming surfaces for subsequent waterproofing.</li><li>&gt; Protection of metallic structures.</li><li>&gt; Liquid waterproof membrane for bicomponent systems.</li><li>&gt; Superficial waterproof protection for concrete elements.</li></ul>
<b>INSTRUCTIONS FOR USE</b>	<ul style="list-style-type: none"><li>&gt; Pinturasfalt should be applied on clean surfaces. Presence of dust, oil, lime or any other pollutant may reduce adherence and detriment Pinturasfalt's properties. Sandblasting is highly recommended prior to painting. For an optimum performance of the product follow the next steps:<ul style="list-style-type: none"><li>• Mix the paint vigorously in the container before applying it.</li><li>• Apply it with a spray gun, brush or roller.</li><li>• Apply uniform layers. Let the first layer dry completely before applying the next one.</li></ul></li></ul>
<b>COVERAGE RATES</b>	<ul style="list-style-type: none"><li>&gt; The coverage rates are determined by the type of application. They can range between 0,15 and 0,3 kg/m<sup>2</sup> per coat, depending on the solution proposed.</li></ul>

# PINTURASFALT IA-22

Solvent-based asphaltic paint

## SPECIFICATIONS

Characteristics	Unit	Standard	MIN	MAX
Brookfield viscosity at 25°C	cP	NIE-008	2500	5000
Inflammability in open vessel	°C	UNE 104281-1.12	25	--
Density at 25°C		UNE 104281-5.4	1,00	1,01
Non-volatile material	%	UNE 104281-3.7	75	--
Volatile organic compounds	g/l	ISO 11890-1	--	200
<b>Characteristics of the residue</b>		EN 13399		
Dry to touch at 25°C and 50% Hr	h	UNE 104281-5.13	--	4
Dry for repainting at 25°C and 60% Hr	h	UNE 104281-5.13	--	24

## STORAGE

- > The containers should be protected from both frost and overexposure to the sun.
- > Storage temperatures should not be below 5°C nor above 30°C since it could affect the quality of the product.
- > Close tightly the containers after using to prevent solvent evaporation.
- > Flammable product. Keep away from fire.
- > The maximum recommended storage time is 12 months from the manufacturing date. The product should be kept in it's the original undamaged container and tightly closed.

## OTHER RECOMMENDATIONS

- > The product should be applied at temperatures between 10°C - 35°C, avoiding unstable weather conditions.
- > For application indoors, the place should be well ventilated to favor correct curing.
- > Since the paint contains solvents, it should be applied in ventilated places using adequate protective equipment
- > If necessary, solvents can be added to thin it.
- > Pinturasfalt treated surfaces should be protected from direct sunlight.
- > Pinturasfalt is not suitable for applications intended to be in contact with solvents or fuels.



N.B: The recommendations in these technical specifications are purely for guidance and for general situations and Cepsa takes no responsibility whatsoever for misuse. For individual cases, contact Cepsa Technical Department.